

1
B 1
25. (Amended) A process according to claim 24 wherein the paper is SC paper, and wherein colloidal PCC is used in a quantity sufficient to achieve a porosity of at most 0.30 $\mu\text{m}/\text{Pas}$.

31. (Amended) A process according to claim 30 wherein colloidal PCC is incorporated into the paper in an amount of at least about 2% by weight based on the total weight of the paper.

B 2
32. (Amended) Uncoated wood-containing paper containing colloidal precipitated calcium carbonate (PCC).

33. (Amended) Paper according to claim 32 containing colloidal PCC having a BET surface area of 10-100 m^2/g as a filler.

B 3
36. (Amended) Paper according to claim 32 wherein the colloidal PCC is present in an amount of at least about 1 % by weight based on the total weight of the paper.

B 4
43. (Amended) A pigment mixture suitable for paper manufacture and comprising colloidal precipitated calcium carbonate (PCC) having a BET surface area of 10-100 m^2/g in combination with at least one filler selected from the group consisting of: kaolin, calcined kaolin, gypsum, chalk, ground marble, silicate-containing minerals, sulphate-containing minerals, oxide-containing minerals, carbonate-containing minerals, hydroxide-containing minerals, calcium sulfoaluminates, plastic particles and organic pigments.

Please add the following claims:

--46. (New) The process according to claim 25, wherein the paper is SC-A paper.--

B 5
--47. (New) A process for regulating the porosity and printing properties of uncoated wood-containing paper wherein at least about 5% by weight of the pulps is lignin-containing pulp, the process comprising using a sufficient quantity of colloidal precipitated calcium carbonate (PCC)